

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification <sup>5</sup> : C08K 5/05, C08L 75/06, 75/14 C08L 75/16, C08F 2/50 C08F 220/36, 265/06, 283/04 C08G 69/44, B32B 27/36 B05D 3/06</p>	<p>A1</p>	<p>(11) International Publication Number: <b>WO 92/17536</b></p> <p>(43) International Publication Date: 15 October 1992 (15.10.92)</p>
<p>(21) International Application Number: PCT/US92/02712</p> <p>(22) International Filing Date: 2 April 1992 (02.04.92)</p> <p>(30) Priority data: 679,608 3 April 1991 (03.04.91) US</p> <p>(71) Applicant: RED SPOT PAINT &amp; VARNISH CO., INC. [US/US]; 1016 E. Columbia Street, Evansville, IN 47703 (US).</p> <p>(72) Inventor: LAKE, Randall, T.; 6711 Heritage Drive, Newburgh, IN 47630 (US).</p> <p>(74) Agents: REEVES, Charles, R. et al.; Woodard, Emhardt, Naughton, Moriarty &amp; McNett, Bank One Center Tower, Suite 3700, 111 Monument Circle, Indianapolis, IN 46204 (US).</p>	<p>(81) Designated States: AT (European patent), AU, BB, BE (European patent), BF (OAPI patent), BG, BJ (OAPI patent), BR, CA, CF (OAPI patent), CG (OAPI patent), CH (European patent), CI (OAPI patent), CM (OAPI patent), CS, DE (European patent), DK (European patent), ES (European patent), FI, FR (European patent), GA (OAPI patent), GB (European patent), GN (OAPI patent), GR (European patent), HU, IT (European patent), JP, KP, KR, LK, LU (European patent), MC (European patent), MG, ML (OAPI patent), MN, MR (OAPI patent), MW, NL (European patent), NO, PL, RO, RU, SD, SE (European patent), SN (OAPI patent), TD (OAPI patent), TG (OAPI patent).</p> <p><b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>	
<p>(54) Title: UV CURABLE HARDCOAT COMPOSITIONS AND PROCESSES</p> <p>(57) Abstract</p> <p>Described is a preferred UV curable coating composition comprising (exclusive of any solvent present): (a) about 5% to 90% by weight of an acrylated aliphatic urethane having a molecular weight of about 500 to 2000 and formed by the reaction of a multifunctional acrylate with a molecular weight of about 190 to 500 and containing at least three polymerizable unsaturated groups per molecule, with an aliphatic urethane based on a polymer of allyl carbomonocycle diisocyanate with alkanepolyol polyacrylates; (b) about 5% to 30% by weight of a multifunctional acrylate having a molecular weight of about 170 to 1000 and containing at least two polymerizable unsaturated groups per molecule; and (c) a photopolymerization initiator and/or sensitizer. Also described are preferred processes and coated articles involving the preferred coating compositions.</p>		

803

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MN	Mongolia
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GN	Guinea	NL	Netherlands
BJ	Benin	GR	Greece	NO	Norway
BR	Brazil	HU	Hungary	PL	Poland
CA	Canada	IT	Italy	RO	Romania
CF	Central African Republic	JP	Japan	RU	Russian Federation
CG	Congo	KP	Democratic People's Republic of Korea	SD	Sudan
CH	Switzerland	KR	Republic of Korea	SE	Sweden
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
DE	Germany	MC	Monaco	TC	Togo
DK	Denmark			US	United States of America

-1-

## UV CURABLE HARDCOAT COMPOSITIONS AND PROCESSES

BACKGROUND OF THE INVENTION

The present invention relates generally to ultraviolet (UV) cured coatings, and more particularly to UV curable coating compositions, processes of their use, and as well to coated articles resulting therefrom.

Conventionally cured hardcoat finishes have several disadvantages. In general, the coating materials and the curing agent must be applied separately, in a particular sequence and at particular relative levels. Because both the proportions of the ingredients and the timing of their application is critical, conventionally cured hardcoats have been difficult and costly to apply, especially with the consistency and uniformity required in current commercial applications.

UV cured coatings overcome several disadvantages associated with conventional hardcoat finishes. In particular, UV curable coating compositions may be premixed, e.g. the polymerization initiator is added to the active ingredients by the manufacturer when the coating is produced, and not by the coating user when the coating is about to be applied. Thus, mixing and measurement errors can be avoided and a more consistent product can be obtained.

Despite their many advantages, UV curable coating compositions themselves pose problems which must be addressed. For example, typical UV hardcoats are high molecular weight, highly crosslinked films which are formed from the highly reactive acrylate functionality. As such, known UV hardcoats have suffered from limited durability, low solids content and cured resin shrinkage. They have also required high doses of UV light to cure. Other UV hardcoats

-2-

formulated in an attempt to overcome these problems typically suffer from some combination of loss of abrasion and scratch resistance, poor processability and unsatisfactory durability. A need therefore exists for a UV curable product  
5 which is conveniently processable and which forms cured coatings exhibiting improved physical and chemical properties, e.g. scratch and abrasion resistance, and durability.

-3-

## SUMMARY OF THE INVENTION

The applicant's invention now addresses these needs and provides in one preferred embodiment a scratch resistant UV curable coating composition. This compositions comprises:

5 (a) 5% to 90% by weight of an acrylated aliphatic urethane having a molecular weight of between about 500 and 2000 and formed by the reaction of (i) a multifunctional acrylate with a molecular weight of between about 190 and 500 and containing at least three polymerizable unsaturated groups

10 per molecule, with (ii) an aliphatic urethane based on a polymer of allyl carbomonocycle diisocyanate with alkanepolyol polyacrylates; (b) 5% to 30% by weight of a multifunctional acrylate having a molecular weight of between about 170 and 1000 and containing at least two polymerizable

15 unsaturated groups per molecule; and (c) a photopolymerization initiator and/or photopolymerization sensitizer. The composition can also optionally include a solvent. However, unless otherwise specified, percents by weight set forth in this application are calculated exclusive

20 of any solvent present. More preferred compositions can also include suitable light stabilizing agents, e.g. hindered amine and/or benzotriazole derivatives, and also antioxidant materials.

Additional preferred embodiments of the invention relate

25 to coated articles and coating processes resulting from and involving the use of applicant's preferred coating compositions.

One object of the invention is to provide improved ultraviolet curable coating compositions giving coatings and

30 coated articles demonstrating superior chemical and physical properties such as chemical resistance, weather resistance, abrasion resistance, scratch resistance, stain resistance, heat resistance and adhesion.

Another object of the invention is to provide processes

-4-

for coating articles, e.g. plastic articles, exhibiting improved physical and chemical properties.

Still another object of the present invention is to provide a coated article exhibiting superior physical and  
5 chemical properties.

Another object of this invention is to provide coating processes and compositions which enable convenient and consistent, uniform processibility.

Further objects and advantages of the present invention  
10 will be apparent from the following description and appended claims.

-5-

## DESCRIPTION OF PREFERRED EMBODIMENTS

For the purposes of promoting an understanding of the principles of the invention, reference will now be made to certain embodiments and specific language will be used to describe the same. It will nevertheless be understood that no limitation of the scope of the invention is thereby intended, such alterations and further modifications and applications of the principles of the invention as described herein being contemplated as would normally occur to one skilled in the art to which the invention relates.

As indicated above, one preferred embodiment of this invention relates to a UV curable coating composition. In this regard, Formula I, set forth below, shows starting materials and compositional ranges for preferred coating compositions of the invention. The compositional ranges are given as percent by weight of the composition excluding any solvent which is included.

Formula I:

	Acrylated aliphatic urethane	(5-90%)
20	Multifunctional acrylate	(5-30%)
	Photopolymerization initiator/sensitizer	(3-15%)
	Hindered amine light stabilizer	(0.1-7.5%)
	Benzotriazole	(0.1-7.5%)
	Antioxidant	(0.1-3.0)
25	Flow additive	(0.1-5.0%)

The acrylated aliphatic urethanes according to the invention contain about 5% to about 95% by weight of prereacted multifunctional acrylate and the balance in the aliphatic urethane. More particularly, to obtain the acrylated aliphatic urethanes, a multifunctional acrylate having a molecular weight of about 190 to about 500 and containing at least 3 polymerizable unsaturated groups per

-6-

molecule (e.g., pentaerythritol triacrylate, diphenyl erythritol tetraacrylate, and trimethylolpropane triacrylate) is prereacted with an aliphatic urethane based on a polymer of allyl carbomonocycle diisocyanate with alkanepolyol polyacrylates. The acrylate having at least three polymerizable groups provides an acrylated aliphatic urethane giving final coatings demonstrating good surface hardness, for example as evidenced by steel wool scratch resistance.

The preferred acrylated aliphatic urethane has a final molecular weight of about 500 to about 2000. More preferably, the acrylated aliphatic urethane has a molecular weight of about 800 to about 1000, with those having a molecular weight of about 800 being most preferred in work to date. These preferred acrylated aliphatic urethanes provide coatings of good weather and thermal crack resistance. Further, these acrylated aliphatic urethanes provide advantageous application solids, curing rates and material compatibility.

The acrylated aliphatic urethane may be obtained commercially. For example, EBECRYL 8301, available from Radcure Specialties, Inc. of Atlanta, Georgia has been highly preferred in work to date.

Exclusive of any solvent present, as indicated above, the acrylated aliphatic urethane constitutes about 5% to 90% by weight of the coating composition. More preferably, this acrylated aliphatic urethane makes up about 50% to about 90% of the composition, most preferably about 80%. These preferred levels have provided good weather and thermal crack resistance, as well as advantageous viscosity, material capacity and cure rates.

As will be understood, the particular multifunctional acrylate employed will depend upon the desired application viscosity and other properties. The preferred multifunctional acrylates are of the reactive diluent type, have a molecular weight of about 170 to about 1000, and



-7-

contain at least two polymerizable unsaturated groups per molecule. Representative multifunctional acrylates thus include ethylene glycol di(meth)acrylate, 1,6-hexanediol diacrylate, pentaerythritol triacrylate, pentaerythritol  
5 tetra acrylate, trimethylolpropane triacrylate, tetraethleneglycol diacrylate, and the like, and mixtures thereof, with light-stable materials, e.g. 1,6-hexanediol diacrylate, being more preferred.

The preferred coating composition includes the  
10 multifunctional acrylate in an amount of about 5% to about 30% by weight, with the range of about 10% to about 20% being more preferred. These preferred levels provide compositions of good compatibility which give coatings of excellent thermal crack resistance.

15 As those practice in these areas will appreciate, many photopolymerization initiators will be suitable for the invention. These include, for instance, benzophenone, benzion, benzionmethyl ether, benzion-n-butyl ether, benzion-iso-butyl ether, propiophenone, acetophenone,  
20 methoxyphenylglyoxylate, 1-hydroxycyclohexyl phenyl ketone, 2,2-diethoxyacetophenone, ethylphenylpyloxylate, phenanthraquinone, and the like, and mixtures thereof. In work thus far, 1-hydroxycyclohexyl phenyl ketone has been more preferred.

25 The photopolymerization initiator and/or sensitizer will be included in an amount sufficient to obtain the desired cure response. In preferred compositions of the invention, the photopolymerization initiator or sensitizer is included in amounts of about 3% to about 15% by weight. The range of  
30 about 5% to about 8.5% is more preferred, with about 6% being most preferred so far. As indicated, however, the amount of initiator and/or sensitizer included will vary based upon many factors such as the cure rate and level of scratch resistance desired. For additional information as to  
35 photopolymerization initiators and sensitizers, reference can

-8-

be made to C. G. Roffey, Photopolymerization of Surface Coatings, Chapter 3: "Photo-initiators and photo-sensitizers", John Wiley & Sons Ltd (1982), which is hereby incorporated by reference.

5       The coating composition also preferably includes other materials such as light stabilizers, e.g. suitable hindered amines and/or benzotriazole derivatives, as well as antioxidants. These materials will be included in varying amounts in accordance with the particular use or application  
10       desired. When included, their amounts will be sufficient to provide increased weatherability yet still obtain adequate cure response for the composition. In more preferred compositions, hindered amine, benzotriazole, and antioxidant have been included in amounts of about 1-6%, 0.5-2.5%, and  
15       0.25-1.5%, respectfully, and in particularly preferred compositions about 0.7%, 0.5% and 0.5% by weight, respectively.

As stated, the coating composition also optionally includes a suitable inert solvent. Representative such  
20       solvents include ester solvents, e.g. ethyl acetate, butyl acetate, and the like, ketone solvents, e.g. acetone, methylisobutylketone, methylethylketone, and the like, alcohols, e.g. butyl alcohol, and the like, and aromatic solvents, e.g. toluene, xylene, and the like. The amount of  
25       solvent included will vary in accordance with the particular application at hand. For instance, for spray applications, higher levels of solvent will typically be included, while for roll applications, lower levels of inert solvent, if any, will be employed. In any event, the inert solvent will  
30       constitute from 0% to about 95% by weight of the coating composition, and in more preferred coating compositions about 40% to 60%.

As will be understood, the coating composition can also include other conventional additives. For instance, it can  
35       contain polymeric or silicone coating surface improvers, flow

-9-

improvers, dyes, pigments, flatting agents (e.g. wax-coated or non-wax-coated silica or other inorganic materials), etc. In more preferred compositions, flow improver is included at a level of about 0.3-2%, and in one especially preferred composition, the flow improver Byk 301, available from  
5 BYK-CHEMIE, of Wallingford, Connecticut, has been included.

As to its use, the coating composition can be applied by any conventional coating method as known in the art. For example the composition can be applied directly to the  
10 substrate or over another previously-cured (e.g. paints or primers) or uncured (e.g. in the case of tie coats) coating. The topcoat material is advantageously used at about 0.3 mils to about 3.0 mils of cured film thickness, with more preferred cured film thicknesses being those around about 1  
15 mil.

Once applied, the coating composition can be cured by irradiation with ultraviolet rays as is known to those skilled in the art. In this regard, the irradiation is continued until curing is complete, with preferred exposure  
20 times typically being less than 300 seconds. Curing temperatures can range from room temperature to the heat distortion temperature of the substrate, while curing distances are typically between about 2 and 18 inches from the UV source.

25 An ultraviolet light source having a wavelength range of between about 1800 Angstroms and 4500 Angstroms is preferred for curing the topcoat. For example, sunlight, mercury lamps, arc lamps, zenon lamps, gallium lamps, and the like may be used, but high pressure or ultrahigh pressure mercury  
30 lamps with power outputs of between about 30 W/cm and 400 W/cm provide particularly advantageous rapid cures.

A high pressure mercury lamp having an intensity of about 30 W/cm to 400 W/cm is preferred, for a total exposure of between about 300 and 16000 mJ/cm<sup>2</sup> as measured by a compact  
35 radiometer at 60 to 1200 mW/cm<sup>2</sup> and about 75 to 4000 mJ as

-10-

measured by a UVIMAP, with a preferred exposure of about 3000 mJ/cm<sup>2</sup> as measured by a compact radiometer at 260 mW/cm<sup>2</sup> and about 700 mJ as measured by a UVIMAP. These preferred curing processes have provided good through cure, and have  
5 ensured advantageous coatings which resist premature yellowing and demonstrate desirable thermal crack resistance. Moreover, these advantageous cures have been achieved over a surprisingly wide range of exposures. Accordingly, the preferred compositions are readily and  
10 highly conveniently processible. Previously known UV curable compositions have demonstrated serious deficiencies in this regard, a problem long recognized in the industry leading to increased production costs and wastes of time and materials.

For the purposes of promoting a further understanding of  
15 the invention and its preferred features and advantages, reference will now be made to the following specific examples and tables. It will be understood that these examples and tables are given by way of illustration and are not restrictive of the invention.

#### EXAMPLE 1

##### 20 Preparation of Preferred UV Curable Coating Composition

In order to prepare a UV curable coating composition in accordance with the invention, items 1 and 2 of Formula II below were charged into a clean stainless steel vessel  
25 equipped with a stirrer. Thereafter, ingredients 3 through 9 were added under agitation until a clear homogeneous mixture was obtained. This composition was designated "Topcoat A".

-11-

FORMULA II

	<u>Part by weight</u>
1. Isopropanol	588.1
2. Butanol	17.8
5 3. 1-Hydroxycyclohexyl phenyl ketone	23.7
4. Hindered amine light stabilizer	5.9
5. Benzotriazole	2.4
6. Antioxidant	2.4
7. Acrylated aliphatic urethane*	320.5
10 8. 1,6 Hexanediol diacrylate	43.2
9. "Byk 301" flow improver	3.6

\*"EBECRYL 8301", based on polymer of alkyl carbon monocycle diisocyanate with alkanepolyol polyacrylate prereacted with an acrylated polyol.

EXAMPLE 2

15

Production of Topcoated Plastic Molded Article

The above-described Topcoat A was applied to polycarbonate resin lenses by spray to allow 23 microns of cured coating thickness. Thereafter, the material was  
20 irradiated with a high pressure mercury lamp of  $120 \text{ W/cm}^2$ , with the substrate positioned eight inches from the light source for an exposure of  $3000 \text{ mJ/cm}^2$  in air.

The thus obtained topcoated polycarbonate resin lens had a clear appearance. The product was evaluated by exterior  
25 decorative standards, and superior results were obtained as set forth in Table 1.

-12-

TABLE 1

	<u>Evaluated Item</u>	<u>Evaluated Method</u>	<u>Results</u>
	Scratch Resistance	0000 Steel Wool Rubs	Passable
	Adhesion	Peel Test ASTM	No loss
5	Abrasion Resistance	Taber Abrader, CS-10, 500g load, 300 cycles	Passable
	Water Resistance	32 degrees Centigrade, 240 hour immersion	Passable, 2ndary adhesion OK
10	Thermal Shock Resist.	4 hrs. water immersion 4 hrs. -29°C Steam blast on scribe	Passable
	Heat Resistance	120°C, 2 hrs.	No cracks
	Resistance to Water & Soap Spotting	Discoloration	Passable
15	Resist. to Acid Spots	No dulling/color change	Passable
	Chemical Resistance	Motor Oil, Tar remover Windshield Wiper Fluid Antifreeze, Motol Fuel	Passable
20	Weather Resistance	EMMA (QUE) 925 kJ, 3.5 years equivalence	Passable

### EXAMPLE 3

#### Comparative Coating Material

A comparative topcoat was prepared in the same manner as in Topcoat A in Example 1, except the acrylated aliphatic urethane was replaced with one of a molecular weight of 2279. The resulting material was designated "Topcoat B".

### EXAMPLE 4

#### Comparative Coated Article

Topcoat B was applied and cured as was Topcoat A in Example 2. The resultant coated article was evaluated by the same conditions as in Example 2, and the results set forth in Table 2 were obtained:

-13-

TABLE 2

<u>Evaluated Item</u>	<u>Results of Evaluation</u>
Scratch Resistance	Noticeable Scratches
Adhesion	No loss
5 Abrasion Resistance	Unacceptable
Water Resistance	Passable Secondary adhesion OK
Thermal Shock Resistance	Passable
Heat Resistance	Unacceptable
Resistance to Water	Passable
10        & Soap Spotting	
Resistance to Acid	Passable
Spotting	
Chemical Resistance	Passable
Weather Resistance	Passable

- 15        It was thus demonstrated that coating compositions including acrylated aliphatic urethanes with molecular weights above about 2000 provide less desirable coatings.

-14-

## CLAIMS

What is claimed is:

1. An ultraviolet curable coating composition,  
comprising, exclusive of any solvent present:
  - 5 about 5% to about 90% by weight of an acrylated aliphatic urethane having a molecular weight of between about 500 and 2000 and formed by the reaction of
    - (i) a first multifunctional acrylate with a  
molecular weight of about 190 to about 500 and containing  
10 at least three polymerizable unsaturated groups per molecule, with
    - (ii) an aliphatic urethane based on a polymer of  
allyl carbomonocycle diisocyanate with alkanepolyol  
polyacrylates;
  - 15 about 5% to about 30% by weight of a second multifunctional acrylate having a molecular weight of about 170 to 1000 and containing at least two polymerizable unsaturated groups per molecule; and  
a photopolymerization initiator or sensitizer.
- 20 2. A coating composition according to claim 1 and further comprising a hindered amine light stabilizer.
3. A coating composition according to claim 2 and further comprising a benzotriazole light stabilizer.
4. A coating composition according to claim 3 and  
25 further comprising an antioxidant.
5. A coating composition according to claim 1, and also comprising a suitable solvent.
6. A coating composition according to claim 5, which,  
exclusive of said solvent, is comprised about 50% to about  
30 90% of said acrylated aliphatic urethane.



-15-

7. A coating composition according to claim 6, which, exclusive of said solvent, is comprised about 10% to about 20% of said second multifunctional acrylate.

8. A coating composition according to claim 7, which, exclusive of said solvent, is comprised about 3% to about 15% of said photopolymerization initiator or sensitizer.

9. A coating composition according to claim 8, wherein said acrylated aliphatic urethane has a molecular weight of about 800 to about 1000.

10. A coating composition according to claim 9, wherein said acrylated aliphatic urethane is Ebecryl 8301.

11. A coating composition according to claim 10, and also including a hindered amine and a benzotriazole light stabilizer.

12. A coating composition according to claim 11, and also including an antioxidant.

13. A method for forming a durable scratch resistant coating on an article, comprising the steps of:

(a) applying to the article an ultraviolet curable coating composition including, exclusive of any solvent present:

about 5% to about 90% by weight of an acrylated aliphatic urethane having a molecular weight of between about 500 and 2000 and formed by the reaction of

(i) a first multifunctional acrylate with a molecular weight of about 190 to about 500 and containing at least three polymerizable unsaturated groups per molecule, with

(ii) an aliphatic urethane based on a polymer

-16-

of allyl carbomonocycle diisocyanate with  
alkanepolyol polyacrylates;  
about 5% to about 30% by weight of a second  
multifunctional acrylate having a molecular weight of  
5 about 170 to 1000 and containing at least two  
polymerizable unsaturated groups per molecule; and  
a photopolymerization initiator or sensitizer;

and,

(b) irradiating and thereby curing the applied  
10 composition.

14. A method according to claim 13 wherein said  
ultraviolet curable composition further comprises a solvent,  
and a hindered amine and a benzotriazole light stabilizer.

15. A method according to claim 14 wherein said  
15 ultraviolet curable composition further comprises an  
antioxidant.

16. A method according to claim 15 wherein:  
exclusive of said solvent, said curable composition  
is comprised about 50% to about 90% by weight of said  
20 acrylated aliphatic urethane, and about 10% to about 20% by  
weight of said second multifunctional acrylate.

17. A method according to claim 16, wherein said  
acrylated aliphatic urethane has a molecular weight of about  
800 to about 1000.

25 18. A method according to claim 17, wherein said  
acrylated aliphatic urethane is Ebecryl 8301.

19. A scratch resistant plastic product which comprises  
a plastic article and a top coating layer, characterized in  
that said top coating layer is a cured layer of an

-17-

ultraviolet curable coating composition comprising, exclusive of any solvent present:

- about 5% to about 90% by weight of an acrylated aliphatic urethane having a molecular weight of between about 500 and 2000 and formed by the reaction of
- 5 (i) a first multifunctional acrylate with a molecular weight of about 190 to about 500 and containing at least three polymerizable unsaturated groups per molecule, with
- 10 (ii) an aliphatic urethane based on a polymer of allyl carbomonocycle diisocyanate with alkanepolyol polyacrylates;
- about 5% to about 30% by weight of a second multifunctional acrylate having a molecular weight of about 170 to 1000 and containing at least two
- 15 polymerizable unsaturated groups per molecule; and a photopolymerization initiator or sensitizer.

20. A scratch resistant product according to claim 19 wherein said ultraviolet curable coating composition further comprises a solvent, and a hindered amine and a benzotriazole light stabilizer.

21. A scratch resistant plastic product according to claim 20 wherein said ultraviolet curable coating composition further comprises an antioxidant.

25 22. A scratch resistant plastic product according to claim 21 wherein:

exclusive of said solvent, said ultraviolet curable coating composition is comprised about 50% to about 90% by weight of said acrylated aliphatic urethane, and about 10% to about 20% by weight of said second multifunctional acrylate.

30

23. A scratch resistant plastic product according to

-18-

claim 22, wherein said acrylated aliphatic urethane has a molecular weight of about 800 to about 1000.

24. A scratch resistant plastic product according to claim 23, wherein said acrylated aliphatic urethane is  
5 Ebecryl 8301.

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US92/02712

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) : Please See Extra Sheet.

US CL : 522/075, 096, 174; 427/054.1, 012; 428/423.1; 524/379, 391; 528/066.

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 522/075, 096, 174; 427/054.1, 012; 428/423.1; 524/379, 391; 528/066.

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS: Ebecryl 8301; ally (meth) acryloyl; allyl diisocyanate and (meth) acrylate; urethane or polyurethane

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category <sup>a</sup>	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US,A, 4,393,187 (Boba et al) 12 July 1983. The abstract and the example.	1-9, 13-17, 19-23
Y	US,A, 4,128,600 (Skinner et al) 05 December 1978. The abstract and column 7, lines 43-59.	1-9, 13-17, 19-23
Y	US,A, 4,511,596 (Berner) 16 April 1985. Column 20, lines 59-68 and column 23, lines 61-68.	2-4, 14, 15, 20, 21

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	* T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
* A* document defining the general state of the art which is not considered to be part of particular relevance	* X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
* E* earlier document published on or after the international filing date	* Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
* L* document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (to specified)	* Z*	document member of the same patent family
* O* document referring to an oral disclosure, use, exhibition or other means		
* P* document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

06 JULY 1992

Date of mailing of the international search report

03 AUG 1992

Name and mailing address of the ISA/  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. NOT APPLICABLE

Authorized officer

SUSAN BERMAN

Telephone No. (703) 308-0040

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US92/02712

A. CLASSIFICATION OF SUBJECT MATTER:  
IPC (5):

C08K 5/05; C08L 75/06, 75/14, 75/16; C08F 2/50, 220/36, 265/06, 283/04; C08G 69/44; B32B 27/36; B05D 3/06.